

Release Paper

Two Side Coated Differential Release

Code : DR6

A two side solventless siliconised 3:1 differential white glassine release.

TYPICAL PROPERTIES	MEASUREMENT	TARGET	RANGE
Substance	gsm	62	59 → 65
Caliper	μ	53	49 → 54
Elmendorf tear	mN	275 min	
MD	mN	300 min	
CD			
Tensile Strength			
MD	kN/m	5.0 min	
CD	kN/m	2.2 min	
Transparency	%	45 min	
Release			
1 side	g/25mm	12	8 → 18
2 side	g/25mm	30	25 → 40
Minimum of 10g/25mm difference between sides			