

Economy Thermal Transfer

Code : ETT

A white wood-free Thermal Transfer topstock. Also suitable for flexographic, letterpress and offset litho printing processes. It can also be used for Ink Jet printing.

Used for primary and secondary labelling applications.

TYPICAL PROPERTIES	MEASUREMENT	TARGET	RANGE
Substance	gsm	73	+/- 3
Caliper	μ	70	+/- 5
Tensile strength			
MD	DaN/15mm	>7.2	
CD	DaN/15mm	>3.9	
IGT varnish	mm	67	+/- 7
Smoothness, BEKK	s	300	+/- 70
Porosity	ml/min	90	+/- 40
CIE whiteness		135	+/- 5
Opacity	%	83	>81

Can be supplied as block-out version for high opacity requirements.

